

Name			Chemical Composition, wt. %					
	JIS	UNS	Cu	Pb	Fe	Sn	Zn	Other Named Elements
Brass	C2700	C27000	63.0~67.0	0.05	0.05	-	Rem.	-
	C2720	C27200	62.0~64.0	0.07	0.07	-	Rem.	-
	C2800	C28000	59.0~63.0	0.10	0.07	-	Rem.	-
Leaded Brass	-	C34000	62.0~65.0	0.8~1.5	0.15	-	Rem.	-
	-	C34500	62.0~65.0	1.5~2.5	0.15	-	Rem.	-
	-	C35000	60.0~63.0	0.8~2.0	0.15	-	Rem.	-
	-	C35300	60.0~63.0	1.5~2.5	0.15	-	Rem.	-
Free Cutting Brass	-	C36000	60.0~63.0	2.5~3.7	0.35	-	Rem.	-
	C3601	C36000	59.0~63.0	1.8~3.7	0.30	(Fe+Sn)0.5	Rem.	-
	C3602	C36000	59.0~63.0	1.8~3.7	0.50	(Fe+Sn)1.2	Rem.	-
	C3603	-	57.0~61.0	1.8~3.7	0.35	(Fe+Sn)0.6	Rem.	-
	C3604	-	57.0~61.0	1.8~3.7	0.50	(Fe+Sn)1.2	Rem.	-
	C3605	-	56.0~60.0	3.5~4.5	0.50	(Fe+Sn)1.2	Rem.	-
Forging Brass	C3712	C37100	58.0~62.0	0.25~1.2	(Fe+Sn)0.8	-	Rem.	-
	C3771	C37700	57.0~61.0	1.0~2.5	(Fe+Sn)1.0	-	Rem.	-
Naval Brass	C4622	C46200	61.0~64.0	0.30	0.20	0.7~1.5	Rem.	-
	C4641	C46400	59.0~62.0	0.50	0.20	0.50~1.0	Rem.	-
	-	C48500	59.0~62.0	1.3~2.2	0.10	0.50~1.0	Rem.	-
High Strength Brass	C6782	-	56.0~60.5	0.50	0.10~1.0	-	Rem.	0.20~2.0Al, 0.50~2.5Mn
	C6783	-	55.0~59.0	0.50	0.20~1.5	-	Rem.	0.20~2.0Al, 1.00~3.0Mn

Also available C5191 / C5441 Phosphor-Branze Bar & Wire, C7541 / C7941 Nickel Silver Bar & Wire.
Composition, percent maximum, unless shown as a range or a minimum.